

Technical Data Sheet

Resin HSC 7600 (Unmodified Epoxy Resin)

Product Description

Unmodified medium viscosity liquid epoxy resin derived from epichlorohydrin and bisphenol A.

Various curing agents are available to cure liquid epoxy resins like at ambient cure conditions (Polyamines, polyamides, amidoamines, cycloaliphatic amines, phenalkamines etc.) and at elevated temperature cure conditions (Anhydrides or other catalytic curing agent).

Features

- Good chemical resistance
- Good thermal resistance
- Excellent adhesion
- Excellent mechanical and electrical properties
- Good pigment wetting

Applications

- Adhesive
- casting and tooling
- civil and building
- composites
- solvent free and high solids coatings
- marine and protective coating
- potting and encapsulation

Product Specifications

Properties	Units	Reference standard	Value
Appearance	Visual	HTP-1	Clear Liquid
Colour	Gardener	ASTM D 1544	<1
Viscosity @ 25°C	mPas	ASTM D 2196	9000 - 12,000
Epoxy Equivalent Weight	gm/eq	ASTM D 1652	180 - 190
Epoxy Index	g/ cc	ASTM D 1652	5.25-5.55
Hydrolysable Chlorine	Ppm	ASTM D 1726	Max 1000

HTP: HSCL Testing Procedure

Processing and Storage

Packaging

HSC 7600 is available in bulk packing of drums, IBC's and container. For handling and pumping the maximum temperature shall not exceed 80°C.

Technical Data Sheet

Safety & Handling

Following instructions needs to be followed strictly.

- Keep working conditions clean. Allow fresh air in, if possible, provide ventilator.
- Avoid contact with human body directly, wear gloves and other personal protective equipment.
- Wash hands carefully with soap. If possible, wash with acetone and alcohol first, then soap and water.
- In case of eye contact, wash with running water for 15 minutes and then seek medical treatment.

Refer MSDS for better instruction on Safety & Handling.

Storage Conditions

HSC 7600 should be stored at room temperature free of moisture, in the original containers kept tightly closed. If haziness or crystallises is observed on opening the can, warm the resin at 45-50°C with stirring to bring back to original conditions. Container once opened should be tightly closed to avoid contamination by foreign materials. The shelf life of the resin is 24 months.

Disclaimer

All recommendations for use of our products, whether given by us in writing, verbally or to be implied from results of tests carried out by us are based on the current state of our knowledge. Notwithstanding any such recommendations the Buyer shall remain responsible for satisfying himself that the products as supplied by us are suitable for his intended process or purpose. Since we cannot control the application, use or processing of the products, we cannot accept responsibility. Therefore, the Buyer shall ensure that the intended use of the products will not infringe any third party's intellectual property rights. We warrant that our products are free from defects in accordance with and subject to our general conditions of supply.

Registered Office:

Hindusthan Speciality Chemicals Limited
(A Subsidiary of DCM Shriram Ltd.)
2nd Floor (West Wing), World Mark 1,
Aerocity, New Delhi 110037, INDIA
Tel: +91 9117020202
E-mail: saleshscl@dcmsriram.com

Factory:

Hindusthan Speciality Chemicals Limited
(A Subsidiary of DCM Shriram Ltd.)
Plot No.:830, GIDC, Jhagadia Industrial Estate,
Jhagadia, Bharuch District,
Gujarat - 393110, INDIA
Website: www.hindusthanspeciality.com